

DOW FILM SPECS

SERIES	THICKNESS	VLT	VLR	UVR	IRR	TSER	WARRANTY	SPEC
ULTRA70	2.5mil	70%	17%	99%	95%	68%	8 years	1.52mX30m
ULTRA25	2.5mil	25%	7%	99%	93%	75%	8 years	1.52mX30m
ULTRA20	2.5mil	20%	9%	99%	93%	82%	8 years	1.52mX30m
ULTRA05	2.5mil	5%	7%	99%	95%	88%	8 years	1.52mX30m
PRO70	2mil	70%	7%	99%	98%	62%	8 years	1.52mX30m
PRO50	2mil	50%	6%	99%	95%	65%	8 years	1.52mX30m
PRO35	2mil	35%	6%	99%	96%	70%	8 years	1.52mX30m
PRO20	2mil	20%	5%	99%	98%	85%	8 years	1.52mX30m
PRO05	2mil	5%	5%	99%	98%	88%	8 years	1.52mX30m
PLUS70	1.8mil	70%	8%	99%	95%	52%	5 years	1.52mX30m
PLUS50	1.8mil	50%	7%	99%	90%	68%	5 years	1.52mX30m
PLUS35	1.8mil	35%	6%	99%	83%	66%	5 years	1.52mX30m
PLUS20	1.8mil	20%	5%	99%	93%	83%	5 years	1.52mX30m
PLUS05	1.8mil	5%	5%	99%	93%	87%	5 years	1.52mX30m

RECOMMENDED SHELF LIFE : 2 years from the date of purchase*

RECOMMENDED STORAGE CONDITIONS : 72°F (22°C) @ 50% RH

*If installing film after recommended shelf-life, re-certification by The Project 3, is required.

- Product performance tolerances for visible light, solar energy, UV rejection and IR rejection values are +/- 5%. Product thickness values are nominal and for guidance only. Our warranty covers defects including: staining, color fading, blistering, and delaminating. Warranty is limited to product defects stated above and does not include installation bubbles, mis-installation, normal wear and tears, accidents, or intentional damages of any kind. The warranty is limited to replacement of defective film.